

1. Is APP TimberAzobe from legal source?

Yes, **APP TimberAzobe** is OLB certified. OLB system (French for Origine et Legalité des Bois) is a system developed by Eurocertifor in 2004 and is a result from customers insisting to have the guarantee that the delivered lumber is effectively legally cut. OLB certified wood products are a step closer towards F. S.C. Certification. APP TIMBER PROMOTES AND STIMULATES THE USE OF LEGAL WOOD

2. Is APP TimberAzobe need to be treated?

No. **APP TimberAzobe**'s heartwood is extremely resistant, even the sapwood also resistant to any preservative.

3. Is APP TimberAzobe kiln dried?

No. **APP TimberAzobe** supply is shipping dried.

4. How is the drying and shrinkage of APP TimberAzobe?

APP TimberAzobe must be dried slowly with marked tendency to surface and end check but warping is not serious. Kiln schedule T2-C2 is suggested for 4/4 stock and T2-C1 for 8/4. Shrinkage green to oven dry: radial 6.0%; tangential 8.8%; volumetric 12.6%.

5. How are the working properties of APP TimberAzobe?

APP TimberAzobe is rather difficult to saw with some dulling, difficult to work with hand and machine tools, tearing of interlocked grain in planing, turns well, glues and finishes well.

6. Is APP TimberAzobe durable?

APP TimberAzobe's heartwood is very durable and highly resistant to termite attack; sapwood liable to powder-post beetle attack. Resistant to marine borers, excellent weathering properties, and has high resistance to wear.